

# FPU 50

## *Limited Availability*

FPU 50 is an impact, abrasion and fatigue resistant semi-rigid material that is a good choice for parts that must withstand repetitive stresses such as living hinges or friction fits.

<b>Tensile Properties</b> ASTM D638, Type V, 10 mm/min	Metric	U.S.
Tensile Modulus	860 ± 110 MPa	125 ± 16 ksi
Ultimate Tensile Strength	29 ± 1 MPa	4.2 ± 0.2 ksi
Tensile Strength at Yield	20 ± 1 MPa	2.9 ± 0.2 ksi
Elongation at Yield	7 ± 1 %	
Elongation at Break	280 ± 15 %	

<b>Flexural Properties</b> ASTM D790-B	Metric	U.S.
Flexural Stress at 5 % Strain, no yielding	32 ± 1 MPa	4.6 ± 0.2 ksi
Flexural Modulus (chord, 0.5-1 % strain)	831 ± 36 MPa	121 ± 5 ksi

<b>Impact Properties</b>	Metric	U.S.
Notched Izod (Machined), 23 °C, ASTM D256	40 ± 5 J/m	0.75 ± 0.09 ft-lb/in
Notched Izod (Machined), -30 °C, ASTM D256	30 ± 6 J/m	0.56 ± 0.11 ft-lb/in
Unnotched Izod, ASTM D4812	No Break	

<b>Thermal Properties</b>	Metric	U.S.
Heat Deflection Temperature @ 0.455 MPa/66 psi, ASTM D648	78 °C	172 °F
Heat Deflection Temperature @ 1.82 MPa/264 psi, ASTM D648	52 °C	126 °F
Coefficient of Thermal Expansion (-40, 40 °C), ASTM E831	129 ppm/°C	72 ppm/°F
Heat Capacity, 23 °C, ASTM E1269	1.48 J/g-°C	0.353 BTU/lb-°F
Thermal Conductivity, ASTM C518	0.138 W/m-K	0.0799 BTU/hr-ft-°F

<b>Electrical Properties</b>	Metric
Dielectric Strength, ASTM D149	13.0 kV/mm
Dielectric Constant, 1 kHz, ASTM D150	3.21
Dissipation Factor, 1 kHz, ASTM D150	0.0131
Volume Resistivity, ASTM D257	1.87E+13 ohm-cm

<b>General Properties</b>	Metric
Hardness, ASTM D2240	71, Shore D
Density, ASTM D792	1.053 g/cm <sup>3</sup>
Density (liquid resin)	1.06 g/cm <sup>3</sup>
Water Absorption, 23 °C, 24 hours, ASTM D570	0.42 %
Water Absorption, 23 °C, long term, ASTM D570	0.75 %

**NOTES**—Results in this data sheet are representative of specific sample generation and testing processes and may vary if the established protocols are not followed. Contact Carbon for the specific process used to generate the test samples to determine each of these values. Tensile and flexural data are average ± 1 standard deviation from 16 specimens; impact data used 10 specimens. The U.S. values are converted from Metric measurements and are for reference only.

The information in this document includes typical values from printing various parts and is intended for reference and comparison purposes only. This information should not be used for testing, design specification or quality control purposes. End-use material performance can be impacted by, but not limited to, design, processing, operating and end-use conditions, test conditions, color, etc. Actual values will vary with build conditions. In addition, product specifications are subject to change without notice.

This information and Carbon's technical advice are given to you in good faith but without warranty. The application, use and processing of these and other Carbon products by you are beyond Carbon's control and, therefore, entirely your own responsibility. Carbon products are only to be used by you subject to the terms of the written agreement by and between you and Carbon.

You are responsible for determining that the Carbon material is safe, lawful, and technically suitable for the intended application, as well as for identifying the proper disposal (or recycling) method consistent with applicable environmental laws and regulations. CARBON MAKES NO WARRANTIES OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR USE, OR NON-INFRINGEMENT. Further, it is expressly understood and agreed that you assume and hereby expressly release Carbon from all liability, in tort, contract or otherwise, incurred in connection with the use of Carbon products, technical assistance and information. Any statement or recommendation not contained herein is unauthorized and shall not bind Carbon. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.